

The performance information listed is for new products and is intended to be used for reference only, and is not complete. Depending on the components, accessories, and options chosen, the actual rating could vary. Confirm ratings for specific products with your supplier or JELD-WEN sales representative.

Builders Clad-Wood Windows											
SERIES	GLAZING	U-FACTOR	CR	No Grids		5/8" Flat GBG, 23/32" Contoured GBG, SDL			N/A		
				SHGC	VT	U-FACTOR	SHGC	VT	U-FACTOR	SHGC	VT
Clad Awning	Clear	0.50	40	0.60	0.62	0.50	0.54	0.56	N/A	N/A	N/A
	Low-E 272	0.37	50	0.32	0.54	0.37	0.29	0.49	N/A	N/A	N/A
	Low-E Argon	0.33	54	0.32	0.54	0.33	0.29	0.49	N/A	N/A	N/A
	Low-E EC	0.32	39	0.27	0.48	0.32	0.25	0.44	N/A	N/A	N/A
	Low-E EC Argon	0.29	42	0.27	0.48	0.29	0.25	0.44	N/A	N/A	N/A
	Low-E 366	0.36	51	0.22	0.49	0.36	0.20	0.44	N/A	N/A	N/A
Clad Casement	Clear	0.50	40	0.60	0.62	0.50	0.55	0.56	N/A	N/A	N/A
	Low-E 272	0.37	51	0.32	0.54	0.37	0.30	0.49	N/A	N/A	N/A
	Low-E 272 Argon	0.33	54	0.32	0.54	0.33	0.30	0.49	N/A	N/A	N/A
	Low-E EC	0.32	40	0.27	0.48	0.32	0.25	0.44	N/A	N/A	N/A
	Low-E EC Argon	0.29	42	0.27	0.48	0.29	0.25	0.44	N/A	N/A	N/A
	Low-E 366	0.36	52	0.22	0.49	0.36	0.20	0.44	N/A	N/A	N/A
Clad Casement Fixed	Clear	0.49	40	0.67	0.70	0.49	0.60	0.62	N/A	N/A	N/A
	Low-E 272	0.34	50	0.36	0.61	0.34	0.32	0.54	N/A	N/A	N/A
	Low-E 272 Argon	0.30	54	0.35	0.61	0.30	0.32	0.54	N/A	N/A	N/A
	Low-E EC	0.29	39	0.30	0.54	0.29	0.27	0.48	N/A	N/A	N/A
	Low-E EC Argon	0.26	42	0.30	0.54	0.26	0.27	0.48	N/A	N/A	N/A
	Low-E 366	0.34	51	0.24	0.55	0.34	0.22	0.49	N/A	N/A	N/A
Clad Casement Geometric	Clear	0.47	39	0.69	0.73	0.47	0.62	0.65	N/A	N/A	N/A
	Low-E 272	0.32	49	0.37	0.63	0.32	0.33	0.57	N/A	N/A	N/A
	Low-E 272 Argon	0.29	51	0.37	0.63	0.29	0.33	0.57	N/A	N/A	N/A
	Low-E EC	0.26	38	0.31	0.56	0.26	0.28	0.51	N/A	N/A	N/A
	Low-E EC Argon	0.24	41	0.31	0.56	0.24	0.28	0.51	N/A	N/A	N/A
	Low-E 366	0.32	49	0.24	0.57	0.32	0.22	0.51	N/A	N/A	N/A
Clad Double-Hung	Clear	0.50	41	0.63	0.65	0.50	0.56	0.58	N/A	N/A	N/A
	Low-E 272	0.36	50	0.33	0.57	0.36	0.30	0.51	N/A	N/A	N/A
	Low-E 272 Argon	0.32	53	0.33	0.57	0.32	0.30	0.51	N/A	N/A	N/A
	Low-E EC	0.31	39	0.28	0.51	0.31	0.25	0.45	N/A	N/A	N/A
	Low-E EC Argon	0.28	42	0.28	0.51	0.28	0.25	0.45	N/A	N/A	N/A
	Low-E 366	0.36	50	0.22	0.51	0.36	0.20	0.46	N/A	N/A	N/A
	Low-E 366 Argon	0.32	53	0.22	0.51	0.32	0.20	0.46	N/A	N/A	N/A

**Builders Clad-Wood Windows**

SERIES	GLAZING	U-FACTOR	CR	No Grids		5/8" Flat GBG, 23/32" Contoured GBG, SDL			N/A		
				SHGC	VT	U-FACTOR	SHGC	VT	U-FACTOR	SHGC	VT
Clad Double-Hung Transom	Clear	0.48	43	0.65	0.68	0.48	0.58	0.61	N/A	N/A	N/A
	Low-E 272	0.34	54	0.34	0.59	0.34	0.31	0.53	N/A	N/A	N/A
	Low-E 272 Argon	0.31	54	0.34	0.59	0.31	0.31	0.53	N/A	N/A	N/A
	Low-E EC	0.29	42	0.29	0.53	0.29	0.26	0.47	N/A	N/A	N/A
	Low-E EC Argon	0.26	45	0.29	0.53	0.26	0.26	0.47	N/A	N/A	N/A
	Low-E 366	0.34	54	0.23	0.53	0.34	0.21	0.48	N/A	N/A	N/A
Low-E 366 Argon	0.30	54	0.22	0.53	0.30	0.21	0.48	N/A	N/A	N/A	
Clad Double-Hung Geometric	Clear	0.48	39	0.69	0.73	0.48	0.62	0.65	N/A	N/A	N/A
	Low-E 272	0.33	49	0.37	0.63	0.33	0.33	0.57	N/A	N/A	N/A
	Low-E 272 Argon	0.29	52	0.37	0.63	0.29	0.33	0.57	N/A	N/A	N/A
	Low-E EC	0.27	38	0.31	0.56	0.27	0.28	0.51	N/A	N/A	N/A
	Low-E EC Argon	0.24	41	0.31	0.56	0.24	0.28	0.51	N/A	N/A	N/A
	Low-E 366	0.32	49	0.24	0.57	0.32	0.22	0.51	N/A	N/A	N/A
Low-E 366 Argon	0.28	52	0.24	0.57	0.28	0.22	0.51	N/A	N/A	N/A	
Clad Sliding Patio Door	Clear	0.47	41	0.57	0.61	0.47	0.50	0.53	0.48	0.50	0.53
	Low-E 270	0.34	51	0.28	0.52	0.34	0.25	0.45	0.36	0.25	0.45
	Low-E 270 Argon	0.30	54	0.27	0.52	0.30	0.24	0.45	0.32	0.24	0.45
	Low-E EC	0.29	40	0.26	0.47	0.29	0.23	0.41	0.31	0.23	0.41
	Low-E EC Argon	0.26	44	0.26	0.47	0.26	0.23	0.41	0.28	0.23	0.41
	Low-E 366	0.33	51	0.21	0.48	0.33	0.19	0.42	0.36	0.19	0.42
Low-E 366 Argon	0.30	54	0.21	0.48	0.30	0.19	0.42	0.32	0.19	0.42	
Clad Sidelite	Clear	0.46	44	0.54	0.57	0.46	0.47	0.49	0.47	0.47	0.49
	Low-E 270	0.34	56	0.26	0.48	0.34	0.23	0.42	0.36	0.23	0.42
	Low-E 270 Argon	0.31	59	0.26	0.48	0.31	0.23	0.42	0.33	0.23	0.42
	Low-E EC	0.30	43	0.25	0.44	0.30	0.22	0.38	0.31	0.22	0.38
	Low-E EC Argon	0.28	47	0.25	0.44	0.28	0.22	0.38	0.29	0.22	0.38
	Low-E 366	0.34	56	0.20	0.45	0.34	0.17	0.39	0.36	0.17	0.39
Low-E 366 Argon	0.31	59	0.19	0.45	0.31	0.17	0.39	0.33	0.17	0.39	

